

Grade Name	Br (KG)	HcB (KOe)	Hci (KOe)	BHmax(MGOe)	Tmax
YX18	8.5-9.0	≥7.8-8.2	≥15-19	16-18	250C / 482F
YX20	9.2-9.6	≥8.2-9.0	≥15-19	19-21	250C / 482F
YX24	9.6-10.0	≥9.2-9.7	≥15-19	22-24	250C / 482F
YXH24	9.5-10.2	≥8.0-9.2	≥18-25	22-24	300C / 572F
YXG26	10.2-10.5	≥9.4-10.0	≥18-25	24-26	300C / 572F
YXG28	10.5-10.8	≥9.5-10.0	≥18-25	26-28	300C / 572F
YXG28B	10.2-11.0	≥5.2-6.5	≥5.5-6.5	26-28	300C / 572F
YXG30	10.8-11.0	≥9.8-10.5	≥18-25	28-30	300C / 572F
YXG30B	10.8-11.0	≥5.2-5.6	≥5.5-6.5	28-30	300C / 572F